

## SUNBELT® 3.2 oz

DeWitt Sunbelt 3.2 oz is a woven polypropylene fabric that provides many years of reliable results. Sunbelt 3.2 oz resists punctures, tears, and weed growth. Sunbelt is formulated to resist UV degradation. The fabric design allows air, water, and nutrients to pass through.

Properties	Test Method	Unit	Minimum Average Roll Value
Material			Polypropylene
Color			Black with Gold Stripe every 12"
Construction Weave			20 x 9.5
Weight	ASTM D 5261	(OZ/SY) GSM	(3.2) 108
Grab Tensile Strength	ASTM D 4632	LBS	Warp 175 Weft 105
Grab Elongation	ASTM D 4632	%	Warp 25 Weft 25
Trapezoid Tear	ASTM D 4533	LBS	Warp 80 Weft 75
Puncture	ASTM D 6241	LBS	500
Water Permeability	ASTM D 4491	GAL/MIN/SF	15
Ultraviolet Exposure	ASTM D 4355	% Strength Retained	70% after 2500 Hrs Xenon Arc Exposure

\*At the time of manufacturing. Handling may change these properties

Date: 06/01/23. This data sheet supersedes all previously issued data.  
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.